



## Timbmet Limited

White Horse Park, Ware Road, Stanford In  
The Vale, Oxon, SN7 8NY, United Kingdom

**T:** 01865 862223

**F:** 01865 864367

**E:** [hello@timbmet.com](mailto:hello@timbmet.com)

## American Ash

**Latin Name** *Fraxinus spp. Fraxinus americana*

Also known White Ash, Canadian Ash



**Wood Type** Hardwood

**Environmental** Not Listed in CITIES , available from well managed sources. FSC<sup>®</sup> available

**Distribution** White Ash occurs in Canada from Nova Scotia to South Western Ontario and in America from New England, the Middle Atlantic and Central states.

**The Tree** A medium sized tree 15m to 18mm tall with a diameter of 0.75m

**The Timber** The sapwood is almost White in Colour and the heartwood varies from pale yellow streaked with brown to light brown to reddish-brown. Grain is usually straight with a coarse texture.





**Timbmet Limited**

White Horse Park, Ware Road, Stanford In The Vale, Oxon, SN7 8NY, United Kingdom

**T:** 01865 862223

**F:** 01865 864367

**E:** [hello@timbmet.com](mailto:hello@timbmet.com)

<b>Colour</b>	Yellow Brown to Light Brown
<b>Density</b>	594kg/m <sup>3</sup> – 670kg/m <sup>3</sup> when dried
<b>Durability</b>	Non Durable
<b>Movement</b>	Small
<b>Drying</b>	Dries fairly easily with very little degrade
<b>Texture</b>	Coarse Uniform
<b>Working Qualities</b>	Machines well, good in nailing screwing and gluing. Can be stained to a very good finish.
<b>Uses</b>	A relatively strong timber, pale in colour, used in interior joinery.

