



Timbmet Limited

White Horse Park, Ware Road, Stanford In The Vale, Oxon, SN7 8NY, United Kingdom

T: 01865 862223

F: 01865 864367

E: hello@timbmet.com

Southern Yellow Pine

Latin Name *Pinus palustris*, *Pinus Elliottii*, *Pinus echinata*, *Pinus Taeda*

Also known as Southern Yellow Pine, Southern Pine



Wood Type	Softwood
Environmental	Not Listed in CITIES , available from well managed sources. FSC available
Distribution	<i>P.palustris</i> ranges from South East Virginia to Florida and Texas occurring along the coasts of the Atlantic and Gulf of Mexico. <i>P.elliottii</i> occurs in the same area but is more restricted to South Carolina to Florida
The Tree	Both species attain a height of 30m and a diameter of 0.75m



**Timbmet Limited**

White Horse Park, Ware Road, Stanford In The Vale, Oxon, SN7 8NY, United Kingdom

T: 01865 862223

F: 01865 864367

E: hello@timbmet.com

The Timber	The sapwood is a lighter in colour than the heartwood which is yellowish brown to reddish brown. Both species are typical of the hard pine class being resinous with the growth rings usually well marked by the contrast between the light coloured early wood and the dense darker coloured late wood , which produces a rather coarse texture
Colour	Yellowish to Reddish brown
Density	670kg/m ³ when dried (can vary by 20%)
Durability	Non Durable
Movement	Medium
Drying	Dries readily with little degrade.
Texture	Medium
Working Qualities	Machines moderately easily , but the resin is often troublesome tending to clog saw teeth and cutters. Saws with teeth of fairly long pitch tend to reduce the effect of resin. A good finish obtainable and the wood can be glued , nailed and screwed satisfactorily, fair results with paint and other finishing treatments
Uses	Internal Joinery

