



## Timbmet Limited

White Horse Park, Ware Road, Stanford In  
The Vale, Oxon, SN7 8NY, United Kingdom

**T:** 01865 862223

**F:** 01865 864367

**E:** [hello@timbmet.com](mailto:hello@timbmet.com)

## Beech Unsteamed

**Latin Name** *Fagus Sylvatica*

Also known European Beech



<b>Wood Type</b>	Hardwood
<b>Environmental</b>	Not Listed in CITIES , available from well managed sources. FSC <sup>®</sup> -C019582 available.
<b>Distribution</b>	Central Europe and UK
<b>The Tree</b>	Reaches a height of 45m with a clear bole of 15m but on average 9m with a with a diameter averaging 1.2m
<b>The Timber</b>	There is no distinction by colour between sapwood and heartwood colour can vary from pale brown to reddish brown. Typically straight grained with a fine even texture
<b>Colour</b>	Reddish brown to deep reddish brown





**Timbmet Limited**

White Horse Park, Ware Road, Stanford In The Vale, Oxon, SN7 8NY, United Kingdom

**T:** 01865 862223

**F:** 01865 864367

**E:** [hello@timbmet.com](mailto:hello@timbmet.com)

<b>Density</b>	670kg/m <sup>3</sup> – 720kg when dried
<b>Durability</b>	Perishable
<b>Movement</b>	High
<b>Drying</b>	Although it dries fairly rapidly, it is moderately refractory tending to twist, warp, check, split and shrink considerably.
<b>Texture</b>	Fine
<b>Working Qualities</b>	Works fairly readily and is capable of a good smooth finish, turns well takes glue readily.
<b>Uses</b>	Interior Joinery , Furniture Mouldings

